

## RonaDeck EcoPath UV

### Aggregate and recycled rubber resin bound surfacing system



#### FEATURES

- SuDS compliant—highly permeable paving
- UV stable resin will not discolour
- Natural aggregates
- Uses rubber granules recycled from truck tyres
- Alternative to conventional paving
- Flexible
- Installed by approved contractors
- Low maintenance

#### Description

RonaDeck EcoPath UV is a resin bound aggregate surface for pedestrian traffic. RonaDeck EcoPath UV surfaces are decorative and functional, seamless and slightly flexible. The open matrix allows water to drain through to the base, eliminating water ponding and allowing water to drain to planted areas or land drains. The system is designed to be SuDS compliant reducing the impact of development on flood risk and allowing water to flow into water courses. Edgings created from brick, stone, timber or steel should be installed to retain and protect the resin bound surfacing.

RonaDeck EcoPath UV comprises RonaDeck EcoPath UV Resin, a two component UV stable polyurethane resin which binds aggregate and recycled vulcanised rubber granules. RonaDeck EcoPath UV provides an attractive surface, is strong enough for foot traffic, and is highly porous. RonaDeck EcoPath UV is typically applied to compacted Type 3 aggregate to provide a thin alternative to asphalt or concrete. RonaDeck EcoPath UV is designed for light foot traffic only. It is not designed for road surfacing, drives or car parks.

#### Traffic

#### Foot Traffic After

**14-15 hours @ 20°C**

#### Aggregate

Some aggregates can contain small amounts of iron which can produce rust staining. This naturally occurring iron cannot be identified before use and Ronacrete cannot accept any responsibility for any loss or damage suffered as a result of staining.

#### Appearance

The appearance of samples and of materials supplied by Ronacrete are based on the colour, shade and grading of individual aggregates supplied to Ronacrete by its suppliers. Being largely natural aggregates, the appearance will vary from bag to bag and batch to batch, a uniform appearance should not be expected and cannot be achieved.

# RonaDeck EcoPath UV

## Aggregate and recycled rubber resin bound surfacing system

|  |  |  |
|--|--|--|
| Maintenance  | It is possible to repair localised damage by cutting out and replacing, ideally using the same aggregate as originally supplied. Ageing and weathering of the original may prevent an invisible repair. “Picking out” of some stones is possible but is likely to be minimal and localised. Any major loss of stone should be reported.  |  |
| Slip Resistance  | Application of RonaDeck EcoPath UV Anti-Slip Aggregate will significantly increase the slip resistance of the surface in the wet, without substantial change to appearance and its use may help comply with Health and Safety obligations.   |  |
| Contractors  | RonaDeck EcoPath UV is a specialist product and must only be applied by specialist applicators. Do not apply or allow it to be applied by contractors who do not possess the necessary skills and experience. You should consider appointing a Ronacrete Approved Contractor.  |  |
| Suggested Construction<br>SuDS Compliant Permeable<br>Construction for Footpaths | <p>RonaDeck EcoPath UV System is designed for light foot traffic only, a suggested form of paving construction follows.</p> <p><b>EcoPath UV Surfacing</b><br/>35mm minimum depth of RonaDeck EcoPath UV vulcanised rubber granules and natural aggregate bound with RonaDeck EcoPath UV Resin.</p> <p><b>Granular Sub-base</b><br/>175mm minimum well compacted Type 3 granular sub-base or similar approved</p> <p><b>Optional Impermeable Membrane</b><br/>Impermeable membrane to carry water to infiltration/storage system</p> <p><b>Or</b></p> <p><b>Geotextile Layer</b><br/>Geotextile layer to prevent upward migration of soil</p> <p><b>Capping Layer</b><br/>If required, depending on sub-grade condition</p> <p><b>Sub-grade</b></p> <p>The above information is produced for guidance only, the designer/ contractor should be satisfied that the construction is suitable for the expected traffic and ground conditions.</p> |  |

|            |                                     |      |
|------------|-------------------------------------|------|
| Mix Design | RonaDeck EcoPath UV Resin           | 7kg  |
|            | RonaDeck EcoPath UV Aggregate       | 75kg |
|            | RonaDeck EcoPath UV Rubber Granules | 15kg |
|            | RonaDeck EcoPath Sand               | 7kg  |

# RonaDeck EcoPath UV

## Aggregate and recycled rubber resin bound surfacing system

|                      |  |                            |
|----------------------|--|----------------------------|
| Coverage             | Coverage @ 35mm  | 2.4m <sup>2</sup> (approx) |
|                      | Coverage is based on application to a smooth flat surface and will vary when applied to undulating surfaces, according to compaction, and to the aggregate grading, which can change from batch to batch.  |                            |
| Packaging            | RonaDeck EcoPath UV is supplied as a 104kg batch.  |                            |
|                      | RonaDeck EcoPath UV Resin  | 1 x 7kg                    |
|                      | RonaDeck EcoPath UV Aggregate  | 3 x 25kg                   |
|                      | RonaDeck EcoPath UV Rubber Granules  | 1 x 15kg                   |
|                      | RonaDeck EcoPath Sand  | 1 x 7kg                    |
| Instructions for Use | <ol style="list-style-type: none"><li>1. Place 90kg RonaDeck EcoPath UV rubber granules and kiln-dried aggregate into a clean, forced action mixer, minimum pan capacity 120 litres, Baron E120 mixer or similar.</li><li>2. Scrape all of the contents of RonaDeck EcoPath UV Resin Part B component into the larger Part A container and mix with a drill and helical paddle mixer attachment for 30-45 seconds. Keep mixing time to a minimum to avoid a build up of heat.</li><li>3. Immediately add the mixed resin to the aggregate in the mixer. Mix the aggregate and resin together until all the aggregate is evenly coated with resin. Keep mixing time to a minimum to avoid a build up of heat.</li><li>4. Discharge the mixed resin and aggregate onto the prepared sub-base, level and smooth. Excessive compaction will reduce permeability.</li><li>5. Light rain on the surface of the system is unlikely to damage or affect the surface, see later reference to application in rainy conditions.</li><li>6. Finish the surface with a suitable float.</li><li>7. If required, immediately cast RonaDeck EcoPath UV Anti-Slip Aggregate onto the surface of the wet resin, at the rate of approximately 0.1kg/m<sup>2</sup>. Ensure even coverage to prevent a patchy appearance.</li><li>8. Allow to cure. At 20°C protect against damage by heavy rain for 12 hours and open to traffic after approximately 14 hours at 20°C.</li></ol> |                            |
| Working Temperatures | <p>Working time is affected by temperature including material, air and substrate temperature. At temperatures above 25°C the pot life and working time may be insufficient to allow its proper application.</p> <p>Work should therefore not proceed when product, air or substrate temperature exceed 25°C. The temperature of the substrate must therefore be measured and monitored during application and work should stop when temperature is above 25°C.</p> <p>At low temperatures RonaDeck EcoPath UV Resin will not flow sufficiently to achieve a smooth finish and work should not proceed when air, material or substrate temperature is below 5°C. The surface must not be trafficked until it has gained sufficient strength.</p>  |                            |

# RonaDeck EcoPath UV

## Aggregate and recycled rubber resin bound surfacing system

### Rain During Application

Light rain on the surface of the system is unlikely to cause damage to or affect the surface. Heavy rain is likely to spoil the appearance of the surface. Very heavy rain could wash out resin and aggregate. Therefore application during rain or when rain is anticipated during the cure period is not recommended.

### Shelf Life and Storage

Shelf life of RonaDeck EcoPath UV is 6 months, aggregates have an unlimited shelf life. Store materials in clean, dry, frost free warehouse conditions between 5°C and 25°C. Protect from sunlight.

### Health and Safety

Refer to Safety Data Sheet.

### Site Attendance

When on site Ronacrete representatives are able, if asked, to give a general indication of the correct method of installing a Ronacrete product. It is important to bear in mind that Ronacrete Ltd is a manufacturer and not an application contractor and it is therefore the responsibility of the contractor and his employer to ensure he is aware of and implements the correct practices and procedures to ensure the correct installation of the product and that liability for its correct installation lies with the contractor and not with Ronacrete Ltd.

The information detailed in this leaflet is liable to modification from time to time in the light of experience and of normal product application, and before using, customers are advised to check with Ronacrete Ltd, quoting the reference number, that they possess the latest issue. Any person or company using the product without first making further enquiries as to the suitability of the product for the intended use does so at his own risk, and Ronacrete Ltd can accept no responsibility for the performance of the product, or for any loss or damage arising out of such use.

## Resin Bound and Bonded Surfacing

## Ronacrete

RONL 750 Issue 1 9th March 2016

Ronac House, Flex Meadow, Harlow, Essex CM19 5TD, U.K.  
Tel: +44 (0)1279 638700 [www.ronacrete.co.uk](http://www.ronacrete.co.uk) [technical@ronacrete.co.uk](mailto:technical@ronacrete.co.uk)